



HI-ALLOY TSA - TIG

AIR HARDENING TOOL STEEL WIRE

DESCRIPTION: Hi-Alloy TSA-TIG was designed for the repair of the A-type 5% chrome and D-type high chrome high carbon grades of air hardening tool steels. The high as welded hardness also makes this product good for hardfacing steels where resistance to high abrasion, mild impact, and metal to metal wear are required. It is also suitable for use in both hot and cold working applications.

TYPICAL APPLICATIONS: Repair of extrusion, blanking, coining and forming dies, punches, trimmers, mandrels, construction, mining, and farm equipment.

PROCEDURES: Completely clean the area to be welded, remove all fatigued metal, and round off sharp edges. Slowly and uniformly preheat according to base metal specifications and maintain temperature throughout the welding procedure. Try to position part so welding can be done on a slight incline. Use the smallest diameter filler rod and lowest amperage possible to minimize heating of the part yet providing for a stable arc and suitable weld penetration. Amperage will be dictated by the thickness of the base metal and tungsten diameter. Argon shielding gas is recommended. Skip weld if necessary to distribute heat evenly, do not heat base metal beyond the tempering temperature to avoid loss of hardness. Lightly peen each bead while still red hot to relieve stresses. Allow the part to cool slowly in still air. If welding in a cool environment take measures to provide for slow cooling of the finished part such as use of a furnace or a suitable insulating material. When part cools to about 200° F, post heat to base metal specifications and slow cool to ambient temperature.

AVAILABLE SIZES: .045 1/16 3/32

POLARITY: DC Straight

HARDNESS: As Welded Hardness 45 - 50 RC

DEPOSIT IS HEAT TREATABLE. USE A-2 PROCEDURE.